

Wood Care Yacht Varnish

Transparent yacht varnish with UV filters



THINNING
0-5%



SPREADING RATE
12-13m²/L



TOOLS
brush



DRY TO TOUCH
3-5 hours



It is a high quality transparent solvent borne polyurethane alkyd decorative varnish. It contains UV filters for protection against sun radiation extending the life time of the film. It has superior hydrophobicity making ideal solution for wooden yachts or boats and surfaces nearby the sea like wooden fences, pergolas etc. Suitable for exterior and interior wood surfaces such as doors, windows, frames, pergolas, fences. It presents an exceptional scratch resistance, durability against the salts, excellent application and leveling properties creating a high-build dry film. Its elasticity enables it to support dimensional variations without cracking or flaking.

- » High UV Resistance
- » Superior hydrophobicity
- » High build finishing

TECHNICAL DATA

Binder Type	Alkyd/Polyurethane	
Specific Gravity {ISO 2811} @ 25°C	0.94Kg/L (± 0.02)	
Solids Content (w/w)* {ISO 3251-03}	65% (±3)	
Stormer Viscosity {ASTM D 562-05} @ 25°C	Gloss Satin	80KU (±20) 70KU (±20)
Drying Time (Recorder) {ASTM D-5895}	1.0-3.0h	
Gloss 60° {ISO 2813-99}	Gloss Satin	>95 units 65-75 units
Spreading rate per coat**	12-13m ² /L	

* depending on the finishing.

** depending on the finish, the application conditions and surface absorption.



Interior/Exterior trim varnishes & woodstains including opaque woodstains A/e (S/B).

- Limit Value: 400g/L
- The maximum VOC content of the product in its ready to use condition: 399g/L

Wood Care Yacht Varnish

Transparent yacht varnish with UV filters



SURFACE PREPARATION

The surface must be dry and free of dust, mold or resin. Sand with a suitable abrasive paper, along with the grain, and smooth well the surface.

- » **On new wooden surfaces:** Remove greases or resins with KRAFT BRUSH THINNER, sanding parallel to the grain, removing the dust with a damp, lint-free cloth, apply 1 coat of KRAFT WOOD CARE wood preservative for protection against woodworm and fungi.
- » **On painted surfaces:** Check the surface stability. If it is acceptable apply directly the varnish. If not, remove all old paint or varnish using KRAFT REMOVER and then clean the surface with KRAFT BRUSH THINNER or sand well until their removal with the appropriate sandpaper. After complete drying of the surface and removing all residues, repair all the defective points of the wood with suitable putty. Then apply the varnish.

APPLICATION INSTRUCTIONS

- » Before you start painting, dilute the paint by adding up to 5% by volume KRAFT BRUSH THINNER and stir well.
- » Check the wood moisture before painting. It shall not exceed 10%.
- » Do not apply on wooden surfaces which are in contact with the ground or water.
- » The durability of the film is reduced when applied on horizontal surfaces that are pressed.
- » Appropriate application tool for this product is brush.
- » Apply 2-3 coats of KRAFT WOOD CARE YACHT VARNISH for the best result.
- » Apply it outdoor or in a well-ventilated area.
- » Minimum recoat time is approx. 24-48 hours. The recoating time may vary depending on the weather conditions.
- » The surface drying time is 3-5 hours at 25°C and 50% relative humidity (drying times are longer in wet/cold conditions).
- » Avoid application at temperatures below 5°C or greater than 35°C and relative humidity greater than 60%.

APPLICATION INSTRUCTIONS

- » Close the bucket well to maintain in good condition for future use. Store before and after opening in a cool place and away from sunlight or frost conditions.
- » Clean the tools thoroughly with KRAFT BRUSH THINNER, water and soap.
- » Avoid exposure of the painted surface in rain for 7 days after application.
- » Allow at least 15 days before cleaning and washing newly painted surfaces.

- » You can wash the painted surfaces gently with a soft sponge and water and in cases of bad stains with a mild detergent.

PACKAGING

- » Available in transparent gloss and satin finish in 0.75L and 2.5L containers.

HEALTH SAFETY AND ENVIRONMENTAL INFORMATION

Read label before use. For further information please refer to the Material Safety Data Sheet.

Poison Centre Telephone:

+30 210 7793777

STORAGE

- » Store the product before and after opening at temperatures between 5°C to 35°C.

DISCLAIMER: The above technical data, information, recommendations and guidance are based on scientific and technical knowledge, laboratory studies and long experience. However, the above information is considered to be as indicative and should be reviewed in any case in relation to each specific application conditions. Consequently, the suitability of each product in any application must be evaluated after referring to the updated Technical Data Sheet and to the website www.kraftpaints.gr, as well as after contacting the technical support department, in case of necessity. Our company guarantees the quality of the product itself, whilst in any case the user/applicant is exclusively responsible for any undesirable failures after using the product.

DRUCKFARBEN HELLAS S.A.

ASPROPYRGOS 19 300 ATTICA - GREECE | TEL.: +30 210 55 19 500 - FAX: +30 210 55 19 501
www.druckfarben.gr | www.kraftpaints.gr



Toll-free number

800 111 7700 Monday - Friday, 8.00 am - 04.00 pm

Email: paints.orders@druckfarben.gr